



Bloq





Bloq

Bloq is a fine flatwoven quality belonging within our Comfort Collection. A collection that consists only of soft, voluminous and elegant fabrics.

After introducing Bloq it soon became a well running article. Over the last years it grew further in volume and proved to be successful in almost every European country. To aid this article's success, our development team now launches new contemporary and commercial colours to the colour palette. That makes Bloq available in an astonishing range of 23 colours in total.

Using micro chenille yarns this fabric feels soft and full while beaming with elegance. The laminated heavy fleece backing creates an even more thick and chunky feel to this much wanted upholstery fabric. And while Bloq is piece dyed, woven on an air jet loom and treated with a damp and dirt repellency finish, this is an article that lasts. It is even washable at 30 degrees.

- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 85%PES 15%NY
/ backside 100%PES
/ chenille flatweave

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67



beige 05



blush 92



brown 15



chocolate 17



cognac 28



cream 02



darkblue 48



desert 109



eucalyptus 193



forest 162



grey 65


Please note: colours may vary according to your screen settings.



lightgrey 60



liver 10




mint 50



mustard 06



navy 49




niagara 158



scarlet 141



steel 149



taupe 12



wood 108



zinc 167

Please note: colours may vary according to your screen settings.

Bloq - Article passport

Article of micro chenille yarns for a soft, elegant and full handfeel.
Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	85%PES 15%NY	
Composition backside	100%PES	
Bonding	fleece	
Statistic code	54076130	
Dyeing method	piece dyed	
Available colours	23	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	25.000		min. 12.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4-5		min. 4	min.5	B-C
	middle colours	CTL	grade	4-5		min. 4	min.5	B-C
	dark colours	CTL	grade	4-5		min. 4	min.5	B-C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 141							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 510							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	2.200	858	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	173,8	52,8	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,5	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	22,8	13,9	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	0,0	n/a	n/a	A/A
    		- Dirt and damp prevention treatment applied. - We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing. - Please note that during washing the damp- and dirt prevented treatment will disappear faster.						

