



Fusion

This article Fusion is part of our Comfort Collection. A heavy jacquard woven textile, which is a valuable addition to this collection of soft and elegant fabrics.

Developed by our dedicated team as a fabric that will lift the appearance of any furniture item on its own. The dessin is subtle and can be styled both as an interior basis or accent fabric.

Fusion is a chenille jacquard woven upholstery textile, piece dyed and available in a wide range of bright, contemporary and classic colours.

This heavy and chunky quality is suitable for all types of furniture and creates an elegant, soft and comfortable handfeel.

Due to the chenille yarns, seat depression and shading are unavoidable, this is a product related property. It can be minimized by brushing the fabric on a regular (weekly) base and by using a vacuum cleaner in combination with low power and an upholstery nozzle. This way the chenille pile will go back to its original position.

Fusion is also machine-washable at 30 degrees Celsius.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside n/a
/ chenille jacquard

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67



army 14



blush 92



brandy 127



brass 170



carmine 36



clay 84



cognac 28




copper 126



cream 02



desert 109



frost 213

Please note: colours may vary according to your screen settings.



graphite 66



indigo 90



ivory 101



mustard 06



niagara 158




onyx 169



pale 200



shell 196



steel 149



teal 198



thyme 206



wood 108

Please note: colours may vary according to your screen settings.

Fusion - Article passport


A voluminous jacquard woven quality with heavy chenille yarns creates a soft, elegant and full hand feel.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille jacquard	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	n/a	
Coating	sbr	
Statistic code	54075200	
Dyeing method	piece dyed	
Available colours	24	
Packaging	bubble wrap	






Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	85.000		min. 8.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
gnitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 580							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.124	1.139	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	85,9	70,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	2,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a
    								



Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl