



Enter





Enter

The best way to get in touch with our Comfort collection, is to just Enter. Our Comfort consists of only soft, voluminous, and elegant upholstery fabrics.

Enter is a blend of 95% polyester and 5% nylon. It's a woven quality made with micro-chenille yarns, that creates the pleasantly soft touch. The non-woven backing provides the extra comfort we intended for this fabric.

The colours are carefully developed in a calm colour palette and the tone-in-tone balanced aspect is achieved by a special dye technique.

This fabric, woven on a airjet loom is an example of how magical something simple can be. With this soft quality you will be sure that your everyday customer has exactly the right look and feel for now and the future.

It's easy to upholster and suitable for many styles and applications. It's comforting enough for beds, super easy-going for sofas and machine-washable at 30 degrees Celsius*.

Due to the micro-chenille yarns, sitting mirror and/ or seat depression will be minimized.

You're welcome to Enter.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.


***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition


/ faceside 95%PES 5%NY
/ backside 100%PES
/ chenille flatweave

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery



ashgrey 40




brass 170




burgundy 34



clay 84




darkblue 48



forest 162



graphite 66




grey 65




hazel 96



herb 214




liver 10



mauve 140

Please note: colours may vary according to your screen settings.



ocre 23




oyster 175




powder 209




shell 196



slate 87



taupe 12



wood 108

Please note: colours may vary according to your screen settings.

Enter - Article passport

Enter is a soft and easy going piece dyed upholstery fabric.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	95%PES 5%NY
Composition backside	100%PES
Bonding	non-woven
Statistic code	54075200
Dyeing method	piece dyed
Available colours	19
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	70.000		min. 12.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
dark colours	CTL	grade	4	3	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/B	
	ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL	passed				

Processing specifications

Minimum workable width in centimeters	± 143							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 360							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.333	498	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	167,2	50,5	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,5	1,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	65,9	50,6	n/a	n/a	n/a
Chemical substances	REACH	Centexbel	passed					
	Oeko-Tex, product class II	Centexbel	certified					

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	-0,4	n/a	n/a	A/A

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.



Textaafoam
Expect what's next in furniture fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl