



# Kong





# Kong

This elegant upholstery fabric Kong is in the Textafoam Natura Collection. A collection that stands for luxurious and naturel upholstery fabrics. Kong has a warm, natural look with a refined texture. Its fine weave and matte finish make it soft yet durable, perfect for both sleek and rounded furniture designs.

Kong has been developed to offer you the ultimate combination of the current trend, a soft touch in combination with a highly durable appearance.

With its matte finish and fine structure, it works beautifully on round and oval shapes, ideal for Scandinavian-style furniture. The combination of polyester, nylon and cotton creates a solid and modern textile.

This high-quality upholstery textile is ideal for all types of furniture, like fitted, buttoned and loose fitting. It will lift your sofa, bed, chair or relax-chair. Piece dyed, resulting in a wide, contemporary colourline that fits perfectly into any interior. Due to the construction and different types of yarn, this quality has this a light, elegant bi-colour aspect.

Kong has been woven on an airjet-loom, guaranteeing consistency, excellent texture, and superior quality.

Finished with a light 'kiss'-coating.

Our quality team recommends a minimum seam allowance of minimum 1 cm, and another advice is to overlock all seams for more stability, especially with tight upholstered furniture. For loose fitted upholstery models. Please know that this fine textile is machine-washable at 30 degrees Celsius\*.

- Always be careful with sharp or rough objects such as watches, buckles or Velcro, as they may damage the fabric.
- When a loop does occur, it can be easily pushed back into the fabric with a blunt object.
- Please consult the washing instructions of your furniture or covers before cleaning.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

## Composition

/ faceside 92%PES 5%CO 3%NY  
/ backside n/a  
/ flatweave

## Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



brown 15



cacao 83



cappuccino 11



cognac 28



cream 02



darkblue 48



forest 162



graphite 66



grey 65



ivory 101



lightgrey 60



linen 110


Please note: colours may vary according to your screen settings.



liver 10



mustard 06




onyx 169



shitake 124



steel 149



stone 181



wood 108

Please note: colours may vary according to your screen settings.

Kong - Article passport

Kong is a piece dyed, matt looking, fine structured article.  
Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

|                      |                                                               |  |
|----------------------|---------------------------------------------------------------|--|
| Productgroup         | flatweave                                                     |  |
| Applications         | sofa's, beds, chairs with fitted and loose fitting upholstery |  |
| Composition faceside | 92%PES 5%CO 3%NY                                              |  |
| Composition backside | n/a                                                           |  |
| Coating              | transparent                                                   |  |
| Statistic code       | 58013300                                                      |  |
| Dyeing method        | piece dyed                                                    |  |
| Available colours    | 19                                                            |  |
| Packaging            | transparent plastic                                           |  |

Durability specifications

| Test                                | Test specification                                                                                                                                                                                                                                | Executed by laboratory: | Unit   | Testresult |     | Norm RAL GZ 430/4:2019-01 |                       | Norm DIN EN 14 465:2006-09 |
|-------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------|--------|------------|-----|---------------------------|-----------------------|----------------------------|
|                                     |                                                                                                                                                                                                                                                   |                         |        | Dry        | Wet | DGM                       | DGM+                  |                            |
| Abrasion resistance - yarn breakage | DIN EN ISO 12947-1:2007-04,<br>DIN EN ISO 12947-2:2017-03                                                                                                                                                                                         | CTL                     | cycles | >100.000   |     | min. 12.000               | min. 16.000           | A                          |
| Pilling                             | DIN EN ISO 12945-2:2000-11.<br>2000 cycles                                                                                                                                                                                                        | CTL                     | grade  | 4-5        |     | min. 3-4                  | min. 4                | A                          |
| Colour fastness to light            | DIN EN ISO 105-BO2:2014-11.<br>Process 3, exposure level 5                                                                                                                                                                                        |                         |        |            |     |                           |                       |                            |
|                                     | light colours                                                                                                                                                                                                                                     | CTL                     | grade  | 5          |     | min. 4                    | min.5                 | B                          |
|                                     | middle colours                                                                                                                                                                                                                                    | CTL                     | grade  | 5          |     | min. 4                    | min.5                 | B                          |
|                                     | dark colours                                                                                                                                                                                                                                      | CTL                     | grade  | 5          |     | min. 4                    | min.5                 | B                          |
| Colour fastness to rubbing          | DIN EN ISO 105-X12:2016-11                                                                                                                                                                                                                        |                         |        |            |     |                           |                       |                            |
|                                     | light colours                                                                                                                                                                                                                                     | CTL                     | grade  | 5          | 5   | dry: 4,<br>wet: 3         | dry: > 4,<br>wet: 3-4 | A/A                        |
|                                     | middle colours                                                                                                                                                                                                                                    | CTL                     | grade  | 5          | 5   | dry: 4,<br>wet: 3         | dry: > 4,<br>wet: 3-4 | A/A                        |
|                                     | dark colours                                                                                                                                                                                                                                      | CTL                     | grade  | 4-5        | 4-5 | dry: 4,<br>wet: 3         | dry: > 4,<br>wet: 3-4 | A/A                        |
| Ignitability (cigarette test)       |  BS 5852 part 1 (1979) from<br>The Furniture and Furnishing (Fire)<br>(Safety) regulations:<br>1988 No. 1324. Schedule 4 part 1<br>Ignition source 0: cigarette | CTL                     |        | passed     |     |                           |                       |                            |

Processing specifications

| Minimum workable width in centimeters     | ± 140                                  |                         |        |            |       |                           |          |                            |
|-------------------------------------------|----------------------------------------|-------------------------|--------|------------|-------|---------------------------|----------|----------------------------|
| Roll length in meters                     | ± 35                                   |                         |        |            |       |                           |          |                            |
| Material weight in grams per linear meter | ± 672                                  |                         |        |            |       |                           |          |                            |
| Test                                      | Test specification                     | Executed by laboratory: | Unit   | Testresult |       | Norm RAL GZ 430/4:2019-01 |          | Norm DIN EN 14 465:2006-09 |
|                                           |                                        |                         |        | Warp       | Weft  | DGM                       | DGM+     |                            |
| Tensile strength                          | DIN EN ISO 13934-1:2013-08             | CTL                     | Newton | 2.658      | 1.895 | min. 350                  | min. 400 | A/A                        |
| Tear growth resistance                    | DIN EN ISO 13937-3:2000-06             | CTL                     | Newton | 318,5      | 156,8 | min. 25                   | min. 30  | A/A                        |
| Resistance to seam slippage               | DIN EN ISO 13936-2:2004-07. Load 180 N | CTL                     | mm     | 1,7        | 1,4   | max. 5                    | max. 4   | A/A                        |
| Delamination                              | DIN 53530:1981-02                      | CTL                     | Newton | n/a        | n/a   | n/a                       | n/a      | n/a                        |
| Chemical substances                       | REACH                                  | Centexbel               |        | passed     |       |                           |          |                            |
|                                           | Oeko-Tex, product class II             | Centexbel               |        | certified  |       |                           |          |                            |

Cleaning specifications

| Test                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                        | Test specification                                                        | Executed by laboratory: | Unit | Testresult |      | Norm RAL GZ 430/4:2019-01 |      | Norm DIN EN 14 465:2006-09 |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------|-------------------------|------|------------|------|---------------------------|------|----------------------------|
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |                                                                           |                         |      | Warp       | Weft | DGM                       | DGM+ |                            |
| Dimensional change for washing 30 degrees celcius / air drying                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              | DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08 | CTL                     | %    | -0,4       | -2,0 | n/a                       | n/a  | A/A                        |
| <div></div> <p>- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.</p> |                                                                           |                         |      |            |      |                           |      |                            |



Textaafoam b.v.  
La Défense 11 | 5026 SC Tilburg  
P.O. Box 12 | 5050 AA Goirle  
The Netherlands

T +31(0)13 534 5934  
F +31(0)13 534 7586  
E info@textaafoam.nl  
www.textaafoam.nl