



Macan

Macan is a chenille flatwoven quality, which is in our Comfort Collection. This collection stands for softness, luxurious, voluminous and elegance.

The face-side of Macan exists of 91% virgin polyester, 5% acrylic, 2% wool and 2% linen. A combination of synthetic and naturel yarns, the specialty is that this 'tweed look' is coming from the natural fibres.

This piece-dyed woven upholstery fabric is strong, durable, and therefor suitable for both fitted and loose-fitting upholstery.

With its weight of +/- 810 grams per linear meter it will give the furniture an exclusive and luxurious look & feel. Tweed is becoming trendy again and perfect to combinable with some Textafoam velvets, such as Royal and Seven, or our Fabraa woolen qualities such as Facet and Forward.

Available from stock in a range of modern, trendy and commercial colours. Machine-washable at 30 degrees Celsius*.

Due to chenille yarns, shading and / or sitting mirror may appear, this can be minimized by brushing regularly against the pile with a soft and clean brush.

- Always be careful with sharp or rough objects such as watches, buckles, or velcro as they may damage the fabric.
- When a loop does occur, it can be easily pushed back into the fabric with a blunt object.


***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 91%PES 5%PAC 2%WO 2%LI
/ backside n/a
/ chenille flatweave

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



ashgrey 40



blush 92



brandy 127



brass 170



caramel 16




darkblue 48



darkgrey 68



dolphin 180




ecru 102



hazel 96



ivory 101



lightgrey 60

Please note: colours may vary according to your screen settings.



natural 01



plumb 168



sage 203



taupe 12



thyme 206



wood 108

Please note: colours may vary according to your screen settings.

Macan - Article passport

A chenille flatwoven quality with a 'tweed look' coming from the natural fibres.
Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	91%PES 5%PAC 2%WO 2%LI	
Composition backside	n/a	
Coating	transparent	
Statistic code	54075200	
Dyeing method	piece dyed	
Available colours	18	
Packaging	bubble wrap	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	60.000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 140							
Roll length in meters	± 30							
Material weight in grams per linear meter	± 810							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.894	730	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	117,2	159,1	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,4	1,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a
    								



Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl