



Marshall



Textafoam
Expect what's next in furniture fabrics

| Performance



Marshall

Marshall is an artificial leather quality from our Performance Collection.

This collection only consists of fabrics and leather looks that meet the highest standards in durability and maintenance. Making them long lasting, easy to clean as well as suitable for almost every type of upholstery.

The Marshall quality is resistant to water, UV light, Chlorin and alcohol. A perfect and strong alternative for real leather. Marshall is a great choice for heavy seating-areas such as, but not limited to, restaurants, hotels, waiting areas, holiday homes and caravans.

Marshall passes the BS5852 cigarette (ignition source 0) & match (ignition source 1) and the EN1021 cigarette (part 1) & match (part 2).

This PVC-PU article is strong and durable. We embossed the leather grain with a roller. Available from stock in no less than 10 colours, Marshall will fit your every project design and furniture.

- Please note that no fluor-carbon treatment has been used for this quality, due to the composition it is automatically damp & dirt prevented, stain resistant and easy to clean & maintain.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 97%PVC 3%PU
/ backside 67%PES 33%CO
/ artificial leather polyurethane (pu)+
polyvinylchlorid (pvc)

Suitable for

sofa's, beds, chairs with fitted and loose fitting
upholstery



beige 05 (fr)



black 61 (fr)




chocolate 17 (fr)



cognac 28 (fr)



ivory 101 (fr)



lightgrey 60 (fr)



liver 10 (fr)



plumb 168 (fr)



taupe 12 (fr)



wenge 192 (fr)

Please note: colours may vary according to your screen settings.

Marshall - Article passport

Marshall is an artificial leather quality that will fit your every project design and furniture.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	artificial leather polyurethane (pu)+ polyvinylchlorid (pvc)	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	97%PVC 3%PU	
Composition backside	67%PES 33%CO	
Bonding	woven	
Statistic code	59031010	
Dyeing method	piece dyed	
Available colours	10	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 51.200	min. 0	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	n/a		min. 3-4	min. 4	n/a
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)		BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	Centexbel		passed			
		DIN EN ISO 1021-2:2014. Source: smouldering cigarette	Centexbel		passed			
Ignitability (match test)		BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 5 part 1 Ignition source 1: match flame equivalent	Centexbel		passed			
		DIN EN ISO 1021-1:2014. Source: match flame equivalent	Centexbel		passed			

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 30							
Material weight in grams per linear meter	± 900							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	512	525	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	37,4	55,0	min. 25	min. 30	C/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,4	3,1	max. 5	max. 4	n/a/n/a
Delamination	DIN 53530:1981-02	CTL	Newton	42,8	36,5	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a



Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl