



Prime





Prime

Fabric Prime is a true boucle beauty. Its smooth yarns, soft touch and excellent performance are the perfect ingredients for our Timeless Collection. The timeless collection represents all our creative essentials.

Fabrics that offer the very best value for money and suit every style all year round.

This luxurious yarn dyed upholstery fabric is woven on a jacquard loom. Chenille boucle yarns in the weft direction are perfect for this beautiful upholstery textile.

The multicoloured upholstery textile is unique in its kind and will give the sofa, chair, or bed an exclusive look & feel. Suitable for all types of upholstery and perfect to upholster in many different interiors and styles.

Due to the more rough construction of Prime, we recommend a minimum seam allowance of minimum 1 cm. Another kind advice is to overlock all seams for more stability, especially with tight upholstered furniture.

For loose fitted upholstery models, please know that Prime is machine-washable at 30 degrees Celsius*.

During usage, a certain hairiness may appear, kindly note that this can be taken away with a pilling razor, this has no further influence on the durability or quality of this textile.

Discover the softness and rich appearance of Prime.

- Always be careful with sharp or rough objects such as watches, buckles, or velcro, as they may damage the fabric.
- When a loop does occur, it can be easily pushed back into the fabric with a blunt object.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside 100%PES
/ chenille jacquard

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery




brandy 127



burgundy 34



chocolate 17



darkgrey 68



ecru 102



gold 132



herb 214



hunter 156




lake 221



linen 110



liver 10



magnolia 160


Please note: colours may vary according to your screen settings.



shell 196



taupe 12



zinc 167

Please note: colours may vary according to your screen settings.

Prime - Article passport

Fabric Prime is a true boucle beauty woven on a jacquard loom.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille jacquard	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	100%PES	
Bonding	fleece	
Statistic code	54075300	
Dyeing method	yarn dyed	
Available colours	15	
Packaging	bubble wrap	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 12.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
gnitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 30							
Material weight in grams per linear meter	± 640							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.032	862	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	149,6	172,9	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	4,2	1,4	max. 5	max. 4	B/A
Delamination	DIN 53530:1981-02	CTL	Newton	34,3	21,5	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-1,6	-2,0	n/a	n/a	A/A
 - We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.								



Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl