



Reno





Reno

The Textaafoam Skins Collection contains all kinds of leather alternatives. Reno is a well running quality and therefor our creative team developed several trendy new colours.

In Reno our product development department found the perfect combination of leather aspect and soft fabric sensation. Really an ultimate special feature of this quality.

The backing consists of recycled real leather fibres which brings you this special and unique thick feeling. For the top layer we used a woven micro suede with a nice leather print. Reno is available in 21 contemporary and fresh colours.

Furthermore, Reno is easy to clean and maintain. This article is treated to be damp and dirt repellent. During daily use, the used aspect of this fabric will become more visible. This will not influence the quality or durability in any way.

- Dirt and damp prevention treatment applied.

***Textaafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside 100%LEATHER FIBRES
/ microsuede woven

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



brandy 127



brown 15



burgundy 34



camel 09



cognac 28



desert 109



darkgrey 68



espresso 123



eucalyptus 193



forest 162



graphite 66



hazel 96

Please note: colours may vary according to your screen settings.



liver 10



mocca 13



mustard 06



natural 01



plumb 168



steel 149



taupe 12



thyme 206



turtle 88

Please note: colours may vary according to your screen settings.

Reno - Article passport

Article with special, unique and thick handfeeling due to the recycled leather fibres on the back.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	microsuede woven	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	100%LEATHER FIBRES	
Bonding	flocked leather fibres	
Statistic code	5907000090	
Dyeing method	piece dyed	
Available colours	21	
Packaging	boxes	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	20.000		min. 8.000	min. 16.000	C
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	4		min. 4	min.5	C
	dark colours	CTL	grade	4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4	2-3	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/C
gnitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 644							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.819	903	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	65,3	52,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,0	1,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	91,3	95,2	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a
    		- Dirt and damp prevention treatment applied.						



Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl