



Chic





Chic

Chic is a shiny, luxury and elegant woven velvet, which is in the Textaafoam Performance Collection.

This collection only consists of fabrics that meet the highest standards in durability and maintenance, making them long lasting, easy to clean and suitable for almost every type of upholstery.

Due to an extra finish Chic passes the BS5852 cigarette (ignition source 0) & match (ignition source 1) and the EN1021 cigarette (part 1) & match (part 2).

Chic has a rather shiny aspect providing an unrivalled elegant allure to this wonderful authentic and luxury fabric. Produced and dyed by professional craftsmen, employed by an exclusive European factory specialized in woven velvets. These velvets are durable and strong with a great depth of colour.

Available from stock in a wide range of trendy and commercial colours, Chic will nicely upholster your furniture completely. Or make a perfect combination with other fabrics in our Contract Collection, like Blake, Craft, Facet or Forward.


***Textaafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside n/a
/ woven velvet

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67 (fr)



beige 05 (fr)



cabernet 205 (fr)



caramel 16 (fr)



chocolate 17 (fr)



grey 65 (fr)



khaki 51 (fr)




lightgrey 60 (fr)




navy 49 (fr)



olive 53 (fr)




onyx 169 (fr)



petrol 56 (fr)


Please note: colours may vary according to your screen settings.



plumb 168 (fr)



red 35 (fr)



taupe 12 (fr)



white 104 (fr)

Please note: colours may vary according to your screen settings.

Chic - Article passport

Strong fabric, suitable for intensive use. Velvet with a cloudy aspect and full and dry grip.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	woven velvet	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	n/a	
Coating	transparent	
Statistic code	58013700	
Dyeing method	piece dyed	
Available colours	16	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 8.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	Centexbel		passed				
	DIN EN ISO 1021-2:2014. Source: smouldering cigarette	Centexbel		passed				
Ignitability (match test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 1: match flame equivalent	Centexbel		passed				
	DIN EN ISO 1021-2:2014. Source: match flame equivalent	Centexbel		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 720							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.344	1.208	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	56,3	170,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,0	3,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class IV	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a
    								



Textaafoam 
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl